

Resins for Cold Mounting



- Complete product range
- High Quality Resins
- Fast Mounting
- Cost efficiency

NX MET cold mounting resins selection:



	Standard	Standard +	Standard ++	Standard ++	Standard +++
Standard mounting	Acrylic Polyester	Acrylic Polyester	Acrylic	Acrylic Epoxy	Epoxy Acrylic
	XF10, XF60	XF10, XF60	XF15	XF15, XF25, XF40	XF40, XF25

- **XF10** : Acrylic Resin (Powder & Liquid), translucent, for standard mounting (crystal clear when curing under pressure). Low shrinkage. Curing time : 8 to 10minutes, Max. Temp.: 85°C
- **XF15** : Acrylic Resin(Powder & Liquid), green, hard. Very low shrinkage. Curing time: 5 to 7minutes, Max. Temp.: 78°C
- **XF25** : Acrylic Resin (Powder & Liquid), blue, very hard. No shrinkage. Curing time: 7 to 10minutes, Max. Temp.: 85°C
- **XF40** : Epoxy Resin (Liquid), transparent, very hard. No shrinkage. Curing time: about 12hours at 25°C for **XF40 +XH40**. Max. Temp. : 75°C. (0.5hours at 80°C for **XF40+XH45**. Max. Temp. : 180°C)
- **XF60** : Polyester Resin (Liquid), very transparent, hard. Low shrinkage. Curing time: 2hours à 25°C. Max. Temp.: 50°C



12, allée Pin de St Clair - 38130 Echirolles France

Tel : +33 438 49 28 33 Fax : +33 438 49 27 85

info@nxmet.com

www.nxmet.com

Distributed by

